

# POLYAMIDE 6.6 SPUN, TYPE 200<sup>+</sup>

For Assessing the Colour Fastness

For tests according to:

- + ISO 105
- + ISO 11641
- + ISO 11642

## article 406



### Inspection Standard of article 406

Parameter	specified value adjacent ISO 105-F03:2001-02-15
Appearance	plain weave, white
Material	according to ISO 105-F03:2001-02-15 polyamide 6.6 100 %
Mass per unit	according to ISO 3801 g/m <sup>2</sup> 130 ± 5
Whiteness value	according to ISO 105-J02 Y <sub>10</sub> 86 ± 2
Aqueous extract	according to ISO 3071 pH 7.0 ± 0.5

