

TEST 104 serial number: 29

polyester/cotton, 65/35, soiled with carbon black/olive oil

(STANDARD REFERENCE MATERIAL FOR TECHNICAL TESTS ONLY)

generally:

| according: | swissatest standard soiling |
|---------------------|--|
| suitable: | sensitive to the amount of detergent and to the level of agitation |
| date of production: | January 2024 |
| durability: | February 2026 |
| storing conditions: | must be well packed and kept in the fridge by $< 8^{\circ}$ C. |

specification of base material:

| article 213 | polyester/cotton fabric, 65/35, bleached, without opt. brightener |
|----------------------------|---|
| thread count in cm | warp: 23.5 |
| | weft: 25.0 |
| yarn count in Nm | warp: 34 |
| | weft: 34 |
| weight in g/m ² | 155.0 |
| width in cm | 135.0 |
| Y-value | 88.6 |
| Rem _{460nm} | 86.7 |

specification of soiled fabric:

| soiling | mixture of olive oil and soot olive oil, virgin olive oil soot, carbon pigment as descriped in IEC 60456 |
|----------------------------|--|
| weight in g/m ² | 163.0 |
| width in cm | 140.0 |
| Y-value | 9.7 |
| Rem _{460nm} | 9.7 |

measuring conditions: instrument

illuminant / observer measuring geometry wavelength range filter measuring diameter gloss DC800V (spectrophotometer) D65 / 10° d/8° 420 to 750nm UV barrier at 420nm 26 mm excluded