TEST 108 Serial number: 108-315 6th ED

Test strips according to IEC 60456, (IEC 6th Ed.)
(STANDARD REFERENCE MATERIAL FOR TECHNICAL TESTS ONLY)

Limit date for use: October 2027

Storing conditions: On receipt of a batch of test strips, the strips must be stored at once in a cool, dark place and kept well packed.

Storage temperature: Between -20°C and +5°C.
Packaging: vacuumed

Please note: Before opening a packet of test strips please allow packet to acclimatise to room temperature.

Base material: Cotton fabric, cretonne, bleached, without brightener according IEC 6th Ed.

Tristimulus values Y: unsoiled 90.39 *0.16*

soiling	soiled fabric	cotton 60°C 103.4 g	cotton 40°C 103.4 g	cotton 60°C 51.7 g	cleaning performance 60°C / 40°C	cleaning performance 103.4g / 51.7g	defined cleaning performance values and tolerances 60°C / 40°C	defined cleaning performance values and tolerances 103.4g / 51.7g
Sebum/Pigment	50.0	65.7	62.6	64.7	1.25	1.07	1.22	1.09
s	*0.6*	*1.4*	*1.0*	*1.5*	*0.17*	*0.16*	*± 0.15*	*± 0.12*
Carbon black	25.3	45.2	41.5	43.2	1.23	1.11	1.26	1.15
s	*1.0*	*2.0*	*1.6*	*2.0*	*0.20*	*0.19*	*± 0.20*	*± 0.20*
sterilized protein	20.1	83.9	73.4	76.1	1.20	1.14	1.20	1.16
s	*0.9*	*0.8*	*2.0*	*1.2*	*0.05*	*0.04*	*± 0.15*	*± 0.10*
chocolate / milk	37.1	66.7	61.8	60.8	1.20	1.25	1.32	1.60
s	*0.6*	*1.9*	*2.3*	*2.4*	*0.14*	*0.16*	*± 0.25*	*± 0.40*
Aged Red Wine	40.2	68.3	60.9	61.4	1.36	1.32	1.41	1.37
s	*0.4*	*0.6*	*0.5*	*0.5*	*0.05*	*0.05*	*± 0.12*	*± 0.12*
Sum	172.7	329.9	300.2	306.2	1.25	1.18	1.29	1.28
s	*2.2*	*3.3*	*3.9*	*4.3*	*0.06*	*0.06*	*± 0.12*	*± 0.12*

Washing conditions:

According to IEC 60456, (IEC 6th Ed.)
Washed with Wascator FOM71 CLS
Number of cycles: 5
Detergent IEC-A* / P base powder Batch: 232-867
Dosage: 103.4 g (60°C and 40°C) and 51.7 g (60°C)
Sodium Percarbonate Batch: 25020530-4
TAED Batch: 2141122882
Water hardness: 2.5mmol/l
Load: 5 kg

This test material complies with IEC 60456 and is subject to continuous quality
This document is valid without signature

Measuring conditions:

Instrument:	DC 800V (Spectrophotometer)
Illuminant / observer:	D65 / 10°
Measuring geometry:	d/8°
Wavelength range:	420 to 750nm
UV filter:	UV barrier at 420nm
Measuring diameter:	30mm
Gloss:	excluded

Swissatest Testmaterialien AG, Mövenstrasse 12, CH-9015 St. Gallen, phone +41 71 311 80 55, swissatest.ch